

# LOTADER<sup>®</sup> AX8750

LOTADER<sup>®</sup> AX8750 is a random ethylene-butyl acrylate-glycidyl methacrylate terpolymer.

- Acrylic ester brings softness and polarity, while keeping high thermal stability during processing.
- The high content of acrylic ester leads to high flexibility (low crystallinity) and high impact absorption behaviour.
- Glycidyl methacrylate provides reactivity (versus OH, COOH and NH<sub>2</sub> groups), leading to optimal dispersion during melt mixing with engineering thermoplastics.
- As an ethylene copolymer, LOTADER<sup>®</sup> AX8750 is compatible with LDPE in all proportions, and with almost all other ethylene copolymers.

LOTADER<sup>®</sup> AX8750 is suitable as an additive to improve impact strength of engineering thermoplastics (PPS, PBT, PET) and PC/PBT, PC/PET and PC/ABS alloys. Lotader<sup>®</sup> AX8750 can be used as a compatibiliser for polyesters/polyolefins blends, as bitumen performance enhancer and adhesion promoter onto metallic surface.

## Typical Properties

	Test Method	Unit	Typical Value
Butyl Acrylate Content	FTIR (internal method)	%.-wt.	25
Glycidyl Methacrylate Content	FTIR (internal method)	%.-wt.	5
Melt Index (190°C/2.16kg)	ISO 1133 / ASTM D1238	g/10min.	12
Melting Point	ISO 11357-3	°C	72
Density	ISO 1193 / ASTM D150	g/cm <sup>3</sup>	0.93
Vicat Softening Temperature (10N) <sup>1</sup>	ISO 306 / ASTM D1525	°C	<40
Flexural Modulus <sup>1</sup>	ISO 178 / ASTM D790	MPa	11
Elongation at Break <sup>1</sup>	ISO 527-2 / ASTM D638	%	860
Tensile Strength at Break <sup>1</sup>	ISO 527-2 / ASTM D638	MPa	4

<sup>1</sup>: On compression molded samples.

*The information above is believed to be accurate and represents the best information currently available to us. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to SK Corporation's standard terms and conditions of sale, copies of which are available upon request and which are part of SK Functional Polymer invoices and/or order acknowledgments. Except as expressly provided in SK Corporation's standard terms and conditions of sale, SK Corporation makes no warranty of merchantability or any other warranty, express or implied, with respect to such information, and SK Corporation assumes no liability from its use. Users should make their own investigations to determine the suitability of the information for their particular purposes. SK Functional Polymer is a subsidiary of SK Global Chemical.*

## Processing

Heat stability of acrylate comonomer allows processing temperatures as high as for polyesters (PBT, PET) and PPS.

**CAUTION:** LOTADER® AX8750 reacts with polymers containing maleic anhydride and acid. This reaction may generate gels and can block an extruder if not controlled. Extruders must be thoroughly purged before and after extrusion.

## Storage, Handling & Safety

LOTADER® AX8750 should be stored in dry conditions and be kept out of moisture in an aerated building. Improper storage conditions may cause degradation and could have consequences on physical properties of the product.

Due to its physical properties (Vicat temperature <40°C), it may be possible that the LOTADER® AX8750 shows some caking. This is particularly true during summer time.

Safety data sheet as well as information on handling and storage of the LOTADER® AX8750 are available upon request to your SK Functional Polymer representative.

## Shelf Life

Three years from the date of delivery, in unopened packaging. For any use above this limit, please refer to our technical services.

*The information above is believed to be accurate and represents the best information currently available to us. Your attention is directed to the pertinent Material Safety Data Sheets for the products mentioned herein. All sales are subject to SK Corporation's standard terms and conditions of sale, copies of which are available upon request and which are part of SK Functional Polymer invoices and/or order acknowledgments. Except as expressly provided in SK Corporation's standard terms and conditions of sale, SK Corporation makes no warranty of merchantability or any other warranty, express or implied, with respect to such information, and SK Corporation assumes no liability from its use. Users should make their own investigations to determine the suitability of the information for their particular purposes. SK Functional Polymer is a subsidiary of SK Global Chemical.*